



Most Widely Accepted and Trusted

ICC-ES Report

ESR-2132

ICC-ES | (800) 423-6587 | (562) 699-0543 | www.icc-es.org

Reissued 03/2016

This report is subject to renewal 03/2017

DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION
SECTION: 07 57 00—COATED FOAM ROOFING

REPORT HOLDER:

HENRY COMPANY LLC

**999 NORTH SEPULVEDA BOULEVARD
EL SEGUNDO, CALIFORNIA 90245**

EVALUATION SUBJECT:

PRO-GRADE® 285 ACRYLIC ELASTOMERIC COATING ROOFING SYSTEMS



Look for the trusted marks of Conformity!

“2014 Recipient of Prestigious Western States Seismic Policy Council (WSSPC) Award in Excellence”



A Subsidiary of

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.



ICC-ES Evaluation Report

ESR-2132

Reissued March 2016

Revised June 2016

This report is subject to renewal March 2017.

www.icc-es.org | (800) 423-6587 | (562) 699-0543

A Subsidiary of the International Code Council®

**DIVISION: 07 00 00—THERMAL AND MOISTURE
PROTECTION**
Section: 07 57 00—Coated Foam Roofing
REPORT HOLDER:

HENRY COMPANY LLC
999 NORTH SEPULVEDA BOULEVARD, SUITE 800
EL SEGUNDO, CALIFORNIA 90245
(310) 955-9200
www.us.henry.com

EVALUATION SUBJECT:
**PRO-GRADE® 285 ACRYLIC ELASTOMERIC COATING
ROOFING SYSTEMS**
1.0 EVALUATION SCOPE
Compliance with the following codes:

- 2012, 2009 and 2006 *International Building Code*® (IBC)
- 2012, 2009 and 2006 *International Residential Code*® (IRC)
- 2013 *Abu Dhabi International Building Code* (ADIBC)[†]

[†]The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

- 1997 *Uniform Building Code*™ (UBC)

Properties evaluated:

- Physical properties
- Fire classification
- Wind resistance
- Impact resistance

2.0 USES

The Pro-Grade® 285 Acrylic Elastomeric Coating roofing systems described in this report are Class A and B roof coverings of coated foam plastic insulation, permitted on buildings of any type of construction.

3.0 DESCRIPTION

The Pro-Grade® 285 Acrylic Elastomeric Coating roofing systems consist of Henry Company LLC spray-applied foam plastic insulation and elastomeric coating.

The foam plastic insulation is RT-2035 2.5-3.0 polyurethane foam having a flame-spread rating of 75 or less when tested in accordance with ASTM E84 (UL 723) at a maximum thickness of 4 inches (102 mm) and a

maximum density of 3 pcf (48 kg/m³). The shelf life of the foam plastic liquid components, stored in original unopened containers, is six months for Component A stored at temperatures from 65°F to 85°F (18.3°C to 29.4°C), and six months for Component B stored at temperatures from 50°F to 75°F (10°C to 23.9°C).

The coating is designated as Pro-Grade® 285 Acrylic Elastomeric Coating. The coating has a one year shelf life when stored in a well ventilated space at temperatures up to 120°F (48.9°C).

Foam plastic insulation thickness and density, coating information, and roof covering classification for the various systems are shown in Table 1.

The coated foam plastic insulation roof coverings described in this report comply with the Resistance to Foot Traffic Test in Section 5.5 of FM 4470.

4.0 INSTALLATION
4.1 Deck Preparation:

Roof surfaces must be free of grease, oil, dirt, sediment, moisture, and other foreign materials. All surfaces not to be covered with foam plastic insulation must be masked off or otherwise protected from overspray. All parapets, crickets and valleys must be flashed in accordance with the applicable code. Where precast concrete planks are present, all joints must be taped with minimum 2-inch-wide (51 mm) roofing tape identified as DT-100.

New plywood decks must be primed with an Acryprime-Substrate primer. New concrete decks must be allowed to cure at least 21 days prior to application of the foam plastic insulation. The surface is then primed with a penetrating epoxy primer, Urebond V.

New metals decks are primed with a two-component wash primer. Gaps in end or side laps of the metal decks must be sealed with an approved sealant.

4.2 Application of the Foam Plastic:

The RT-2035 foam plastic insulation is spray-applied to the prepared substrate in 1/2-inch- to 1-inch-thick (12.7 mm to 25.4 mm) passes to the appropriate thickness as noted in Table 1. The wind velocity at time of application must not exceed 12 miles per hour (19.3 km/h), and the ambient temperature must be at least 60°F (33°C). The foam plastic must not be applied over wet substrates or if rain or inclement weather is imminent. The foam plastic insulation is applied in a one-to-one ratio with equipment capable of metering each component within ±2 percent of the design ratio. The full specified thickness of foam plastic insulation

must be applied at one time. If the foam plastic insulation application is terminated before the final thickness is attained, additional foam plastic insulation may be applied within 24 hours, provided the existing foam plastic insulation is primed with Acryprime-Substrate primer and a minimum of 1/2 inch (12.7 mm) of foam plastic insulation is applied in a single pass. The foam plastic insulation must be free of bumps, pin holes and ridges. Any such irregularities must be eliminated.

4.3 Application of Coating:

The coating must be applied in two coats at the appropriate rate as specified in Table 1. The coating must be applied not less than 2 hours, nor more than 72 hours, following application of the foam plastic insulation. The coating must not be applied if rain, fog or inclement weather is imminent or if temperatures below freezing are anticipated within 24 hours of the coating application.

An optional top surfacing material may be applied over Systems 3, 4 and 5 of Table 1. The material consists of No. 6 crushed limestone applied at a rate of 64 pounds per 100 square feet (3.1 kg/m²), embedded into the uncured top coating and covered with Permaguard roof mix applied at a rate of one batch per 100 square feet (9.29 m²). One batch of Permaguard roofing mix consists of 40 pounds (18.1 kg) of dry mix, 4 1/2 gallons (17 L) of water, 1/2 gallon of Permaguard Acrylic Resin and 3/4 ounce (21.3 g) of Colloid 60.

4.4 Existing Roofs:

Roofing system No. 10, as described in Table 1, may be installed over existing roofs, provided the roof deck is either minimum No. 26 gage [0.019 inch (0.483 mm)] steel or a plywood deck as described in footnote 2 of Table 1. The existing roof covering may remain in place, in accordance with IBC Section 1510 or IRC Section R907, if permitted by the building official.

Prior to foaming, the roof surface must be prepared to assure adequate adhesion. All loose rock, cementitious coatings, peeling paint, dirt and debris must be removed by brooming, power vacuuming or wire brushing.

The surface must be primed with an Acryprime-Substrate primer at a rate of 200 square feet (18.6 m²) per gallon (3.78 L) and allowed to cure a minimum of one hour prior to foam application. Spray applications are subject to the same conditions as noted in Section 4.2. Where the existing roof covering is removed to the substrate, the deck must be prepared as set forth in Section 4.1.

4.5 Wind Resistance:

The systems installed in accordance with Sections 4.1 through 4.3 have allowable wind uplift pressures as noted in Table 2.

4.6 Perimeter Flashing:

Edge securement for perimeter flashing shall be in accordance with IBC Section 1504.5 and the manufacturer's instructions.

5.0 CONDITIONS OF USE

The Pro-Grade[®] 285 Acrylic Elastomeric Coating roof coating systems, described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

5.1 Installation and application of the coated foam plastic insulation roof coverings must comply with the

applicable code, the manufacturer's published installation instructions, and this report. In the event of conflicts between the manufacturer's installation instructions and this report, this report governs.

- 5.2 All materials must be applied by personnel trained and approved by Henry Company LLC.
- 5.3 Where moderate or heavy foot traffic occurs for maintenance of equipment or other reasons, the roof covering must be adequately protected to prevent rupture or wearing of the surface.
- 5.4 Foam plastic insulation must be separated from the interior of the building by an approved thermal barrier in accordance with IBC Section 2603.4, 2012 and 2009 IRC Section R316.5.2, 2006 IRC Section R314.5.2 or UBC Section 2602.5.3.
- 5.5 The code official may require a vapor retarder or barrier to be installed. Use of the foam plastic insulation as a vapor barrier is outside the scope of this report.
- 5.6 Flashing must be installed at wall and roof intersections and at gutters and around roof openings.
- 5.7 The roof deck and supporting structure to which the roof covering is attached must be designed to withstand the applicable wind pressures determined in accordance with ASCE 7.
- 5.8 The RT-2035 foam plastic insulation is produced at the Henry Company LLC facility at 2270 Castle Harbor Place, in Ontario California; and the Pro-Grade[®] 285 Acrylic Elastomeric Coating is produced at 1245 Brooks Street, Ontario, California, under a quality control program with inspections by ICC-ES.

6.0 EVIDENCE SUBMITTED

- 6.1 Data in accordance with the ICC-ES Acceptance Criteria for Spray-applied Foam Plastic Insulation (AC377), dated April 2016.
- 6.2 Reports of physical property tests in accordance with ASTM D6083.
- 6.3 Reports of impact resistance tests in accordance with Section 5.5 of FM 4470.
- 6.4 Reports of tests in accordance with ASTM E84, ASTM E108 (UL 723), and UL 1256.
- 6.5 Quality documentation.
- 6.6 Manufacturer's published installation instructions.

7.0 IDENTIFICATION

All material drums and containers are labeled with the manufacturer's name (Henry Company LLC) and address, product designation, shelf life, and the evaluation report number (ESR-2132). Labels for foam plastic insulation also include the flame spread index.

TABLE 1—ROOF COVERING SYSTEMS OF PRO-GRADE® 285 ACRYLIC ELASTOMERIC COATING APPLIED OVER RT-2035 SPRAY-APPLIED POLYURETHANE FOAM PLASTIC INSULATION^{1,9}

SYSTEM NO.	COATING		TOP SURFACING	MINIMUM FOAM PLASTIC THICKNESS (inches)	MAXIMUM FOAM PLASTIC THICKNESS (inches)	MAXIMUM ROOF SLOPE ⁸ (in./horiz. ft.)	ROOF CLASSIFICATION
	Pro-Grade Coating Type	Total Coating Application Rate (gal./100 ft ²)					
1	Pro-Grade® 285	3	Not required	1	4	1	A
2 ^{2,6}	Pro-Grade® 285	3	Granules ³	1½	4	¼	A
3	Pro-Grade® 285	2½	Permaguard ¹⁰	1	4	3	A
4	Pro-Grade® 285	2½	Permaguard ¹⁰	1	4	4	A
5 ^{2,4}	Pro-Grade® 285	2½	Permaguard ¹⁰	1	4	3	A
6	Pro-Grade® 285	3	Granules ³	1	2	Unlimited	A
7 ^{2,4}	Pro-Grade® 285	3	Granules ³	1½	1½	1	B
8 ⁷	Pro-Grade® 285	3	Granules ³	½	4	½	B
9 ²	Pro-Grade® 285	3	Granules ³	¾	4	½	B
10 ^{2,5}	Pro-Grade® 285	3	Granules ³	1	4	4	B
11	Pro-Grade® 285	3	Granules ³	1	4	3	A

For SI: 1 inch = 25.4 mm, 1 gallon/100 square feet = 0.41 L/m², 1 pcf = 16.0 kg/m³, 1 foot = 304.8 mm, 1 pound/100 square foot = 0.0488 kg/m².

¹Except where noted in footnote 2, 5, 6, or 7, roof decks must be noncombustible (cementitious or metal). Steel decks are minimum No. 26 gage [0.019 inch (0.483 mm)].

²Roof deck may be minimum 15/32-inch-thick plywood bonded with exterior glue, with all board edges supported by blocking, tongue-and-groove joints or other approved type of edge support.

³The coating is surfaced with No. 11 roofing granules applied at a rate of 50 pounds per 100 square feet.

⁴Seams in plywood decks must be covered with minimum 12-inch-wide, 90-pound, mineral-surfaced capsheet.

⁵Existing roof may be Class A or Class B gravel or smooth-surfaced BUR with hot roofing asphalt (loose gravel may be removed).

⁶Roof deck may be minimum 15/32-inch-thick plywood bonded with exterior glue, provided the entire deck is covered with 1/4-inch-thick DensDeck with all joints staggered a minimum of 6 inches from the plywood joints.

⁷Roof deck may be 15/32-inch-thick plywood substrate provided the plywood is covered entirely with 90-pound mineral-surfaced capsheet, mechanically attached.

⁸Minimum roof slope is 1/4 inch vertical to each horizontal foot (2.1%).

⁹All roof systems include RT-2035 polyurethane foam plastic at 2.5 to 3.0 pcf.

¹⁰Permaguard top coat as described in Section 4.3.

TABLE 2—WIND RESISTANCE—COATED FOAM ROOF COVERINGS¹

ALLOWABLE WIND UPLIFT (psf)	SUBSTRATE	RT-2035 FOAM PLASTIC INSULATION THICKNESS (inches)
Limited by substrate	Structural concrete	2
105	Steel deck	Deck flutes are filled and covered with 1-inch foam plastic insulation ²

For SI: 1 psf = 0.0479 kPa, 1 inch = 25.4 mm.

¹Coating must be Pro-Grade® 285 Acrylic Elastomeric Coating.

²Assembly must be FM approved.